Sterilized Reinforced Gowns

Disposable Full Body
50 GSM non woven spun bond polypropylene
Reinforced layer on the front chest and full sleeves,
breathable Non-Woven Polyethylene in critical zones

Anti-static, latex free Fluid repellent

Belt to tie at the waist

Ribb cuff on sleeves - soft white sleeves
Binded neckline with extension to tie at the back
EO sterilization

Wrapped into highly absorbent two towels - 30 x 25cm
Made to standard to EN13795-1 & SABS Standards
Fabric tested to ISO 9001:2015
Packed in Carton of 50 gowns

Sizes available - M - XL - larger sizes a surcharge will apply









Oldiy	SOUTH	(8)
PRC		® AFRICA/
		AA

Significant characteristic	Units	Target	LL	UL	Test Method
Spunbond weight	gsm	50	48	52	NWSP 130.1.R0 (15)
Tensile MD @ Break	N/5cm	≥100	100	-	NWSP 110.1.R0 (15)
Tensile CD @ Break	N/5cm	≥100	100	-	NWSP 110.1.R0 (15)
Elonga⊠on MD @ Break	%	70	50	-	NWSP 110.1.R0 (15)
Elonga⊠on CD @ Break	%	70	50	-	NWSP 110.1.R0 (15)
Nail Tear Strength, MD	N	≥60	60	-	NWSP 110.1.R0 (15)
Nail Tear Strength, CD	N	≥60	60	-	NWSP 110.1.R0 (15)
Fabric thickness	mm	0.35	0.30	0.45	NWSP 120.6.R0 (15)
Fibre gauge	denier	2.2	1.95	2.5	

